


TransferRite®
AirMask™

Available roll widths
 48", 54" and 60"

1.22m, 1.37m and 1.52m



ABI AIRMASK TECHNICAL INFORMATION

PHYSICAL PROPERTY	UNITS	METHOD
Thickness	4.3 mils; 109 microns	PSTC-133
Adhesion	7.0 oz/inch; 1.9 N/25mm	PSTC-101
Tensile Strength, MD	5,600 psi; 38.6 N/mm ²	ASTM D882
Tensile Strength, CD	5,000 psi; 34.5 N/mm ²	ASTM D882
Elongation, MD	570%	ASTM D882
Elongation, CD	550%	ASTM D882
Shelf Life*	24 months	

* when stored at 70° F, 50% relative humidity